

Application No. 10/084,028
Filing Date: February 27, 2002
Page: 2

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended): A white, blaxially oriented film with a thickness in the range from 10 to 500 μm and a whiteness of 90 % or more, whose main constituent is at least one crystallizable thermoplastic and which comprises white pigment consisting essentially of at least one rutile-type titanium dioxide as white pigment and at least one optical brightener and at least one soluble blue dye, with or without other additives, and has also at least one other functionality said film exhibiting a light transmittance of up to 85%, measured to ASTM D1003.

2. (Original): The film as claimed in claim 1, wherein the crystallizable thermoplastic is a polyethylene terephthalate, polybutylene terephthalate, polyethylene naphthalate, bibenzoyl-modified polyethylene terephthalate, or a mixture of these.

3. (Original): The film as claimed in claim 1, wherein the concentration of the white pigment present is in the range from 2.0 to 25.0% by weight based on the weight of the thermoplastic.

4. (Original): The film as claimed in in claim 1, wherein the optical brightener present comprises at least one benzoxazole derivative, triazine derivative, phenylcoumarin derivative, or bisstearyl biphenyl derivative, in amounts of from 10 to 50 000 ppm based on the weight of the crystallizable thermoplastic.

Application No. 10/084,028

Filing Date: February 27, 2002

Page: 3

5. (Previously Presented): The film as claimed in claim 1, which has gained at least one other functionality by being provided with a flame retardant and/or with UV stabilizers (UV absorbers), and/or has been coated so as to be sealable, and/or has been coated on one or both surfaces, and/or has been corona-treated on one or both sides.

6. (Original): The film as claimed in claim 5, wherein the concentration of the UV absorber is in the range from 0.01 to 5.0% by weight, and the concentration of the soluble dye is in the range from 10 to 10 000 ppm.

7. (Original): The film as claimed in claim 5, wherein the UV absorbers present are 2-hydroxybenzophenones, 2-hydroxybenzotriazoles, organonickel compounds, salicylic esters, cinnamic ester derivatives, resorcinol monobenzoates, oxanilides, hydroxybenzoic esters, sterically hindered amines, or triazines, preferably 2-hydroxybenzotriazoles or triazines, or in particular 2-(4,6-diphenyl-1,3,5-triazin-2-yl)-5-hexyloxyphenol or 2,2'-methylenebis(6-(2H-benzotriazol-2-yl)-4-(1,1,2,2-tetramethylpropyl)phenol).

8. (Original): The film as claimed in claim 5, wherein the flame retardant present is an organic phosphorus compound.

9. (Original): The film as claimed in claim 8, wherein the organic phosphorus compound is a carboxyphosphinic acid or anhydride thereof.

10. (Previously Presented): The film as claimed in claim 8, wherein the organic phosphorus compound is bis(5-ethyl-2-methyl-2-oxo-2 λ^5 -[1,3,2]dioxaphosphinan-5-ylmethyl)-methanephosphonate.

Application No. 10/084,028

Filing Date: February 27, 2002

Page: 4

11. (Original): The film as claimed in claim 1, wherein a hydrolysis stabilizer is present, in the form of phenolic stabilizers, alkali metal/alkaline earth metal stearates, and/or alkali metal/alkaline earth metal carbonates, in amounts of from 0.01 to 1.0% by weight.

12. (Original): The film as claimed in claim 11, wherein the phenolic stabilizer is present in amounts of from 0.05 to 0.6% by weight and having a molar mass above 500 g/mol.

13. (Original): The film as claimed in claim 1, wherein regrind is present.

14. (Withdrawn): A process for producing a white, biaxially oriented film with a thickness in the range from 10 to 500 μm whose main constituent is at least one crystallizable thermoplastic, which comprises extruding a crystallizable thermoplastic with at least one rutile-type titanium dioxide as white pigment and with at least one optical brightener, and with other substances providing functionality, to give a flat melt film, quenching and solidifying the same with the aid of a chill roll to give substantially amorphous prefilm, then reheating this film and stretching the same at least once longitudinally and transversely, then heat-setting the film at temperatures of from 200 to 280 $^{\circ}\text{C}$, and finally cooling and winding up the film.

15. (Withdrawn): The process as claimed in claim 14, wherein the film is given at least one other functionality by being provided with a flame retardant and/or with UV stabilizers and/or with at least one sealable layer, and/or by being coated on one or both surfaces, and/or by being corona-treated on one or both sides, and has a soluble dye alongside the optical brightener.

Application No. 10/084,028
Filing Date: February 27, 2002
Page: 5

16. (Withdrawn): The process as claimed in claim 14, wherein the film is produced by metering the rutile-type titanium dioxide, the optical brightener, and the other substances providing functionality into the extruder.

17. (Withdrawn): The process as claimed in claim 16, wherein the rutile-type titanium dioxide, the optical brightener, and the other substances are added by way of masterbatch technology.

18. (Withdrawn): The process as claimed in claim 14, wherein use is made of regrind.

19. (Previously Presented): The film as claimed in claim 1, wherein the dye is present in an amount of from 10 to 10,000 ppm, based on the weight of the crystallizable thermoplastics.

20. (Currently Amended): The film as claimed in claim 19, wherein the blue dye is ~~Sudan Blue 2~~ 1, 4-bis-(butylamino)-anthraquinone dye.

21. (Previously Presented): The film as claimed in claim 1, wherein the crystallizable thermoplastic has a polyethylene glycol content of 1 % by weight or more and the film is thermoformable.